Hermpac Hardwood Decking

TABLE OF CONTENTS

Specification Details 2
Clauses 2
- Scope 2
- Timber Species & Grade 2
- Decking Profile 3
- Decking Finish & Coating 6
- Co-operation 7
- Workmanship 7
- Delivery & Handling 7
- Preparation 8
- Installation 8
- Fixing 9
- Completion 12

Compliances 12

SMARTSPEC

1 Specification Details

Trade Sections: Carpentry, Landscaping
Description:
Keywords: Carpentry, Herman Pacific, Hermpac, hardwood, hardwood deck, hardwood decking, deck, decks, decking, timber, timber deck, timber decking, decking timber, gapped timber deck, gapped timber decking, wood, wooden deck, wooden decking, wood decking, solid wood, solid hardwood, solid hardwood deck, solid hardwood decking, timber species, hardwood species, wood species, Kwila, Purpleheart, Vitex, Greenheart, Angelique, grip tread, grip-tread, grip tread decking, grip-tread decking, watershed profile decking, reeded profile decking, Herman Pacific Watershed Hardwood Decking,

2 Clauses

2.1 Scope

Help Note:
For further information and technical advice, go to www.hermpac.co.nz, email: technical@hermpac.co.nz, or call 09 421 9840.

For technical information on products to attach to this project, please visit productspec.co.nz/en/supplier/hermpac.

2.1.1 Scope

Supply and install Hardwood Decking from Hermpac, as specified herein, complete with all accessories and trim, to the areas identified on the drawings. All aspects of this work shall be in complete accordance with Hermpac Decking technical literature and fixing guide (check www.hermpac.co.nz, email: technical@hermpac.co.nz, or call 09 421 9840 for the latest editions), other relevant product manufacturers' recommendations, and as shown on the drawings.

No substitutions are permitted for the specified Hardwood Decking from Hermpac.

2.2 Timber Species & Grade

Help Note:
For further information and technical advice, go to www.hermpac.co.nz, email: technical@hermpac.co.nz, or call 09 421 9840.

2.2.1 Accoya/Accoya Grey

Class 1 durable timber. Hermpac Accoya® is New Zealand grown Radiata pine modified by the proprietary non-toxic acetylation process. The acetylation modification makes Accoya® class one

SMARTSPEC

durable and provides improved dimensional stability. Accoya® Grey is naturally dyed Accoya® eliminating the need to coat the timber.

2.2.2 Kanda

Hardwood Decking shall be manufactured from Kanda Brun *(Beilschmiedia congolana),* Select & Better grade, kiln-dried solid hardwood.

2.2.3 Kwila

Hardwood Decking shall be manufactured from Kwila (*Intsia bijuga*), Select & Better grade, kiln-dried solid hardwood.

2.2.4 Purpleheart

Hardwood Decking shall be manufactured from Purpleheart (*Peltogyne - species pluralis*), Select & Better grade, kiln-dried solid hardwood.

2.2.5 Vitex

Hardwood Decking shall be manufactured from Vitex (*Vitex cofassus*), Select & Better grade, kiln-dried solid hardwood.

2.3 Decking Profile

Help Note:
Decking profile size/specie will be supplied by Herman Pacific subject to availability at time of order. Contact Hermpac for product availability and supply lead times.

Deck surfaces that provide the main access to a building shall have a slip resistance not less than 0.4 when wet.

For further information and technical advice, go to www.hermpac.co.nz, email: technical@hermpac.co.nz, or call 09 421 9840.

2.3.1 HP89 - 65mm x 21mm

Watershed Decking Profile HP89: 65mm wide x 21mm thick. Manufactured from the timber species specified. Installed in accordance with the manufacturer's requirements to the locations and details shown on the drawings. Fixings - refer to Fixing clause.

Installed Location:

2.3.2 HP90 - 90mm x 21mm

Watershed Decking Profile HP90: 90mm wide x 21mm thick. Manufactured from the timber species specified. Installed in accordance with the manufacturer's requirements to the locations and details shown on the drawings. Fixings - refer to Fixing clause.

SMARTSPEC