Dulux AcraTex Texture Coating Systems

TABLE OF CONTENTS

Specification Details 2
Clauses 2
- Scope 2
- AcraTex on Masonry 2
- AcraTex on Tilt-Up & Precast Concrete 14
- AcraTex on Off-the-Form Insitu Concrete 25
- AcraTex on Polystyrene 37
- AcraTex on Flush-Finished Fibre Cement Sheet 49
- AcraTex on Fibre Cement Sheet 65
- AcraTex - Repaint Textured Substrates 76
- Texture System Accessories 77
- Sample 79
- Co-operation 79
- Workmanship 79
- Delivery & Handling 80
- Preparation 80
- Application 85
- Control Joints 86
- Completion 86

Compliances 87

SMARTSPEC

1 Specification Details

Trade Sections: Plasterwork
Description:
Keywords: dulux, acratex, textured paint, texture coating, texture coating systems, Dulux AcraTex Texture Coating Systems, exterior paint coating

2 Clauses

2.1 Scope

Help Note:
Dulux AcraTex Texture Coating Systems are listed in order of substrate type.
Select the required AcraTex Texture Coating System from the relevant substrate type.

2.1.1 Scope

Supply and install the specified Dulux AcraTex Texture Coating Systems as exterior textured plaster coatings to the locations identified on the drawings and as scheduled in this specification, complete with accessories. All aspects of this work shall be in complete accordance with Dulux AcraTex Technical Literature, relevant DuSpec Specification Sheets and Product Data Sheets (check www.duspec.co.nz, or call 0800 800 424 for the latest editions), other relevant product manufacturers' recommendations, and as shown on the drawings.

No substitutions are permitted for Dulux AcraTex Texture Coating Systems.

Refer to other sections of the Specification not covered in this section regarding concrete and masonry structures, waterproofing and tanking requirements, cladding systems, window and door joinery, etc., relevant to Dulux AcraTex Texture System installation and performance.

For technical information on products to attach to this project, please visit productspec.co.nz/en/supplier/dulux.

2.2 AcraTex on Masonry

Help Note:
AcraTex on Masonry includes AAC, brick and/or block masonry substrates. Refer to the specific DuSpec Specification Sheet (click on the DuSpec number for web link).

Dulux AcraTex Texture Coating Systems on new exterior Masonry substrates are listed in the following order:
Tuscany Coarse - Matt finish; High Build Matt finish; Low Gloss finish
Trowel On 1mm - Matt finish; High Build Matt finish; Low Gloss finish

SMARTSPEC

Spray On 2mm - Matt finish; High Build Matt finish; Low Gloss finish
Float Finish - Matt finish; High Build Matt finish; Low Gloss finish.

Contact Dulux Customer Services on 0800 800 424 for further information and technical assistance regarding Dulux AcraTex Texture Coating Systems.

2.2.1 'Tuscany Coarse' Acrylic Texture System - Matt Finish

Dulux AcraTex Acrylic Texture Coating System on New Masonry - 'Tuscany Coarse', Matt.
System: DuSpec NZ_SA09564.
1st Coat: DULUX AcraTex Masonry Render.
2nd Coat: DULUX AcraTex 501/8 AcraPrime HAR Primer.
3rd Coat: DULUX AcraTex 951 Tuscany Coarse.
4th Coat: DULUX AcraTex AcraShield Advance Matt.

A medium textured finish, high-build acrylic texture coating system, applied to properly prepared substrates in accordance with the manufacturer's technical literature.

1st Coat - Render Base Coat - Dulux AcraTex Masonry Render. To a clean, dry and properly prepared substrate; apply a 3mm - 20mm thick coat of Dulux AcraTex Masonry Render and finish to a straight and true surface free from hollows and deviations. Do not apply if temperature is below 5°C or above 30°C or is likely to be outside these limits before the coat is fully cured. Refer to Dulux AcraTex Data Sheet - NZ_DA1515.

2nd Coat - Primer/Sealing Coat - Dulux AcraTex 501/8 AcraPrime HAR Primer. Apply one full coat of Dulux AcraTex 501/8 AcraPrime HAR Primer to the dry base coat by brush, roller or airless spray, to a minimum 75 micron Dry Film Thickness, and allow to dry before applying the specified texture coat. Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying time. Refer to Dulux AcraTex Data Sheet - NZDA01039.

3rd Coat - Texture Coat - Dulux AcraTex 951 Tuscany Coarse. Prior to application ensure that the base coat has been primed and sealed with AcraTex 501/8 AcraPrime HAR Primer and that the sealer is dry. Apply an even coat of Dulux AcraTex 951 Tuscany Coarse over the sealed base coat, and float finish to a uniform, medium-textured pattern. Do not apply if temperature is below 10°C or above 30°C or is likely to be outside these limits before the coat is fully cured. Allow the texture coat to fully cure before the specified top coat is applied. Refer to Dulux AcraTex Data Sheet - NZDA1345.

4th Coat - Top Coat - Dulux AcraTex AcraShield Advance Matt. A mid-build, pigmented, cross-linking, water based 100% acrylic coating; matt finish. Applied by brush and roller, or airless spray. Tinted to the required colour.
One coat, applied over a dry texture coat, to a minimum 75 micron Dry Film Thickness. Do not apply if temperature is below 10°C or above 30°C or is likely to be outside these limits before the coat is fully dry. Refer to Dulux AcraTex Data Sheet - NZDA0978. For some dark, low-opacity colours a second top coat might be required.

Colour:
Location: